



URSA TERRA Plus

Espesor 50 mm

Resistencia térmica 1,35 m²·K/W

Declaración Ambiental de Producto

Parámetro Evaluado	Unidad	Fabricación de los materiales			Fin de vida		
		Produccion	Transporte	Instalacion	Transporte	Proceso	Vertedero
		A1 a A3	A4	A5	C2	C3	C4
Global Warming Potential	Kg CO ₂ equiv.	1,78E+00	7,58E-01	1,94E-01	5,91E-03	0,00E+00	2,21E-02
Stratospheric Ozone Layer Depletion Potential	Kg CFC11 equiv.	1,16E-07	1,45E-09	2,04E-10	1,13E-11	0,00E+00	1,89E-10
Acidification Potential	Kg SO ₂ equiv.	1,03E-02	4,95E-03	6,06E-05	3,66E-05	0,00E+00	9,42E-05
Eutrophication Potential	Kg PO ₄ ³⁻ equiv.	1,36E-03	7,87E-04	3,65E-04	5,79E-06	0,00E+00	1,24E-05
Abiotic Resource Depletion Potential	Kg Sb equiv.	1,38E-02	5,10E-03	5,57E-05	3,98E-05	0,00E+00	8,42E-05
Photochemical Ozone Formation Potential	Kg ethane equiv.	7,24E-04	4,47E-04	5,82E-05	3,11E-06	0,00E+00	1,50E-05
Consumption of renewable primary energy	MJ (lower heating value)	2,66E+00	1,97E-02	5,94E-03	1,54E-04	0,00E+00	1,23E-02
Consumption of non-renewable primary energy	MJ (lower heating value)	3,28E+01	1,07E+01	1,24E-01	8,32E-02	0,00E+00	1,82E-01
Use of non-renewable secondary fuels	MJ (lower heating value)	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
Use of renewable secondary fuels	MJ (lower heating value)	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
Fresh water consumption	m3	1,51E-02	3,12E-04	1,05E-04	2,45E-06	0,00E+00	3,02E-04
Waste production:	Kg	2,80E+00	3,44E-02	2,82E-01	2,68E-04	0,00E+00	1,16E+00
· hazardous	Kg	1,05E-02	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· non hazardous	Kg	2,79E+00	3,44E-02	2,82E-01	2,68E-04	0,00E+00	1,16E+00
· radioactive	Kg	1,53E-03	1,92E-05	3,60E-08	1,51E-07	0,00E+00	0,00E+00
Output materials for	Kg	1,40E-01	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Reusing	Kg	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Recycling	Kg	1,40E-01	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00
· Energy Recovery	Kg	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00	0,00E+00